

XT-EPDM Vapour barrier



Technical specification

Substrate	Ethyl Polymer Diene Monomer (EPDM)
Widths	100mm to 700mm in 50mm increments. Up to 1400. on request
Roll length	20 + 25m
Thickness	0.75mm (-5%/+10%)

Performance information

Reaction to fire	E (Tested to EN 13501-1)
Water vapour permeability (EN 1931)	70,000
Tensile Strength	≥ 6 N/mm ²
Elongation	≥ 350%
Tear resistance	≥ 35N
Density	1.23kg/m ² per mm
Life expectancy	50 Years